



## Technical Data Sheet: HP6600

<b>Product manual</b>	<b>HP6600</b> is an aliphatic urethane acrylate oligomer developed for UV/EB-cured coatings . It imparts hardness, adhesion, toughness, very fast cure response, and non-yellowing characteristics to these applications.	
<b>Product features</b>	Non-yellowing Very fast cure Good Adhesion Hardness and toughness Good Weatherability High Abrasion Resistance	
<b>Suggested application</b>	Coatings, VM Coatings, plastic Coatings, wood	
<b>Specifications</b>	Functional basis (theoretical)	6
	Appearance(By vision)	Little yellow liquid
	Viscosity (CPS/60℃)	800-1900
	Color (APHA)	≤ 100
	Efficient content(%)	75±5
<b>Packing</b>	Net weight 50KG plastic bucket and net weight 200KG iron drum.	
<b>Storage conditions</b>	Resin please keep cool or dry place, and avoid sun and heat; Storage temperature does not exceed 40 ℃, storage conditions under normal conditions for at least 6 months.	
<b>Use matters</b>	Avoid touching the skin and clothing, wear protective gloves when handling; Leak with a cloth when the leak, and wash with ethyl acetate; for details, please refer to the Material Safety Instructions (MSDS); Each batch of goods to be tested before they can be put into production.	